

## ABSTRACT

A thermoelectric material has an average crystal particle size of at most 50 nm and has a relative density of at least 85 %. A method of manufacturing a

5 thermoelectric material includes the steps of preparing a fine powder and sintering or compacting the fine powder under a pressure of at least 1.0 GPa and at most 10 GPa.